



Designation: A270/A270M – 15 (Reapproved 2019)

Standard Specification for Seamless and Welded Austenitic and Ferritic/Austenitic Stainless Steel Sanitary Tubing¹

This standard is issued under the fixed designation A270/A270M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers grades of seamless, welded, and heavily cold worked welded austenitic and ferritic/austenitic stainless steel sanitary tubing intended for use in the dairy and food industry and having special surface finishes. Pharmaceutical quality may be requested, as a supplementary requirement.

1.2 This specification covers tubes in sizes up to and including 12 in. [300 mm] in outside diameter.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 Optional supplementary requirements are provided, and when one or more of these are desired, each shall be so stated in the order.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels](#)

[A480/A480M Specification for General Requirements for](#)

[Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip](#)

[A923 Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels](#)

[A967/A967M Specification for Chemical Passivation Treatments for Stainless Steel Parts](#)

[A1016/A1016M Specification for General Requirements for Ferritic Alloy Steel, Austenitic Alloy Steel, and Stainless Steel Tubes](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

2.2 ASME Standard:

[B46.1 Surface Texture \(Surface Roughness, Waviness, and Lay\)³](#)

[2.3 ASME Boiler and Pressure Vessel Code: Section VIII Pressure Vessels³](#)

2.4 Other Standard:

[SAE J1086 Practice for Numbering Metals and Alloys \(UNS\)⁴](#)

3. Terminology

3.1 Definitions:

3.1.1 *roughness average, Ra, n*—arithmetic average surface roughness normally reported in microinches or microns; a measurement of surface roughness usually performed by moving a stylus in a straight line along the surface, although other methods may be used.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:

4.1.1 Quantity (feet, metres, or number of lengths),

4.1.2 Name of material (austenitic steel tube),

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Sept. 1, 2019. Published September 2019. Originally approved in 1944. Last previous edition approved in 2015 as A270/A270M – 15. DOI: 10.1520/A0270_A0270M-15R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁴ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

- 4.1.3 Process seamless (SML), welded (WLD), or heavily cold worked (HCW),
 - 4.1.4 Size (outside diameter and average wall thickness),
 - 4.1.5 Length (specific or random),
 - 4.1.6 Surface finish (Section 13),
 - 4.1.7 Optional requirements (product analysis, see Section 9; hydrostatic or nondestructive electric test, see Section 11).
 - 4.1.8 Test report required (Certification Section of Specification A1016/A1016M),
 - 4.1.9 Specification designation,
 - 4.1.10 Special requirements, and
- 4.2 Any supplementary requirements.

5. General Requirements

5.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A1016/A1016M, unless otherwise provided herein.

6. Manufacture

6.1 The tubes shall be manufactured by one of the following processes:

6.1.1 Seamless (SML) tubes shall be made by a process that does not involve welding at any stage.

6.1.2 Welded (WLD) tubes shall be made using an automated welding process with no addition of filler metal during the welding process.

6.1.3 Heavily cold worked (HCW) tubes shall be made by applying cold working of not less than 35 % reduction of thickness of both wall and weld to a welded tube prior to the final anneal. No filler shall be used in making the weld. Prior to cold working, the weld shall be 100 % radiographically inspected in accordance with the requirements of ASME Boiler and Pressure Vessel Code Section VIII, Division 1, latest revision, Paragraph UW 51.

6.2 At the manufacturer's option, tubing may be furnished either hot finished or cold finished.

7. Heat Treatment

7.1 All material shall be furnished in the heat-treated condition. The heat treatment procedure, except for S31803, S32003, S32205, S32750, N08926 and N08367, shall consist of heating the material to a minimum temperature of 1900 °F [1040 °C] and quenching in water or rapid cooling by other means.

7.2 N08926 shall be heat-treated to a minimum temperature of 2010 °F [1100 °C] followed by quenching in water or rapidly cooling by other means. UNS N08367 should be solution annealed from 2025 °F [1110 °C] minimum followed by rapid quenching.

7.3 S31803 and S32205 shall be heat-treated in a temperature range of 1870 °F [1020 °C] to 2010 °F [1100 °C] followed by quenching in water or rapidly cooling by other means.

7.4 S32750 shall be heat-treated in a temperature range of 1880 °F [1025 °C] to 2060 °F [1125 °C] followed by quenching in water or rapidly cooling by other means.

7.5 S32003 shall be heat-treated in a temperature range of 1850 °F [1010 °C] to 2010 °F [1100 °C].

8. Chemical Composition

8.1 An analysis of either one length of flat-rolled stock or one tube shall be made for each heat. The chemical composition thus determined shall conform to the requirements given in Table 1.

9. Product Analysis

9.1 When requested by the purchaser, product analysis tolerance in Specification A480/A480M shall apply. The product analysis tolerance is not applicable to the carbon content for material with a specified maximum carbon of 0.04 % or less.

9.2 If the original test for product analysis fails, retests of two additional lengths of flat-rolled stock or tubes shall be made. Both retests for the elements in question shall meet the requirements of the specification; otherwise all remaining material in the heat or lot shall be rejected or, at the option of the producer, each length of flat-rolled stock or tube may be individually tested for acceptance. Lengths of flat rolled stock or tubes that do not meet the requirements of the specification shall be rejected.

10. Mechanical Tests Required

10.1 *Reverse Flattening Test*—For welded tubes, one reverse flattening test shall be made on a specimen from each 1500 ft [450 m] of finished tubing.

11. Hydrostatic or Nondestructive Electric Test

11.1 Each tube shall be subjected to the nondestructive electric test or the hydrostatic test. The type of test to be used shall be at the option of the manufacturer, unless otherwise specified in the purchase order.

12. Permissible Variations in Dimensions

12.1 The following variations in dimensions shall apply:

12.1.1 For tubes with a specified wall thickness of 0.049 in. [1.24 mm] and greater, variations in outside diameter from those specified shall not exceed the amount prescribed in Table 2. For tubes with a specified wall thickness less than 0.049 in. [1.24 mm], the diameter tolerances shall be a matter for agreement by the manufacturer and the purchaser.

12.1.2 When tubing >4 in. [100 mm] outside diameter is ordered, additional ovality may be required for thin wall tubing. Thin wall tubing applies when the specified wall is less than 0.150 in. [3.8 mm]. When thin wall tubing is ordered, the maximum and minimum outside diameter at any cross section shall deviate from the specified outside diameter by no more than twice the permissible variation in outside diameter given in Table 2; however, the mean diameter at that cross section must still be within the given permissible variation.

12.1.3 The wall thickness at any point shall not vary more than 12.5 %, from the specified wall thickness.

12.1.4 Variations in length shall meet the requirements in Table 2 except when the Pharmaceutical Quality Tubing (Supplementary Requirement S2) is specified.

TABLE 2 Permissible Variations in Dimensions

Size, Outside Diameter, in. mm	Permissible variations in Outside Diameter, in. mm		Permissible variations in Cut length, in. mm [^]	
	Over	Under	Over	Under
1.000 25 and under	0.005 0.13	0.005 0.13	¹ / ₈ 3	0
Over 1 25 to 2 50	0.008 0.20	0.008 0.20	¹ / ₈ 3	0
Over 2 50 to 3 75	0.010 0.25	0.010 0.25	¹ / ₈ 3	0
Over 3 75 to 4 100	0.015 0.38	0.015 0.38	¹ / ₈ 3	0
Over 4 100 to 5 ¹ / ₂ 140, excl	0.015 0.38	0.015 0.38	³ / ₁₆ 5	0
5 ¹ / ₂ 140 to 8 200, excl	0.030 0.75	0.030 0.75	³ / ₁₆ 5	0
8 200 to 12 300	0.050 1.25	0.050 1.25	³ / ₁₆ 5	0

[^] The cut tolerances do not apply to Pharmaceutical Tubing in S2 (see paragraph S2.7).

13. Surface Finishes

Mill Finish

Longitudinally Polished Finish

Mechanically Polished Surface Finish

Circumferential (Rotary) Polished Finish

Finish No. 80

Finish No. 120

Finish No. 180

Finish No. 240

Electropolished Finish

14. Product Marking

Maximum Roughness Average (Ra) Surface Finish

15. Packaging

16. Keywords

SUPPLEMENTARY REQUIREMENTS

S1. Intergranular Corrosion Test

Finish

Packaging

Permissible Variations in Dimensions

S2. Pharmaceutical Quality Tubing

Chemistry

Tensile Requirements

Tensile Test

Hardness Requirements

Manipulation Tests

TABLE S2.2 Number of Tubes in a Lot Heat Treated by the Continuous Process

<i>Size of Tube</i>	<i>Size of Lot</i>
<i>2 in. 50 mm and over in outside diameter and 0.200 in. 5 mm and over in wall thickness</i>	<i>not more than 50 tubes</i>
<i>less than 2 in. 50 mm but over 1 in. 25 mm in outside diameter or over 1 in. 25 mm in outside diameter and under 0.200 in. 5 mm in wall thickness</i>	<i>not more than 75 tubes</i>
<i>1 in. 25 mm or less in outside diameter</i>	<i>not more than 125 tubes</i>

TABLE S2.1 Tensile and Hardness Requirements

<i>Grade</i>	<i>US Designation</i>	<i>Tensile Strength min, ksi MPa</i>	<i>Yield Strength min, ksi MPa</i>	<i>Elongation in 2 in. min,</i>	<i>Rockwell Hardness number, max.</i>
TP304	S30400	75 515	30 205	35	B90
TP304	S30403	70 485	25 170	35	B90
TP316	S31600	75 515	30 205	35	B90
TP316	S31603	70 485	25 170	35	B90
	S31803	90 620	65 450	25	C30.5
2205	S32205	95 655	70 485	25	C30.5
2507	S32750	116 800	80 550	15	C32
2003	S32003	90 620	65 450	25	C30

S3. Chemical Cleaning (Passivation)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610 832 9585 (phone), 610 832 9555 (fax), or service.astm.org (e mail) or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel (978) 646 2600 <http://www.copyright.com>